

# Vaseline Spray

Revision: 20/04/2022

Page 1 from 1

## Technical data

Basis	Mixture based on vaseline oil
Consistency	Liquid
Density	Ca. 0,84 g/ml
Viscosity (Brookfield)	29 mPa.s
Welding Load 4 Ball EP test (ASTM D2596)	3136 N (320 kg)
Wear test 4 Ball (ASTM D2266)	< 0.4 mm
Acidity level (text)	Neutral
Solubility in water	Not soluble
Volatile Organic Compounds (VOC)	40 %
Temperature resistance**	-30 °C → 150 °C
Application temperature	5 °C → 30 °C

\* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. \*\* This information relates to fully cured product.

## Product description

Vaseline Spray is a transparent, acid-free lubricating and protective spray based on vaseline oil.

## Properties

- Rust and corrosion-resistant
- Does not drip
- Acid-free
- Water-repellent
- Does not contain silicones
- For in- and outdoor use
- Aerosol can be used in any angle (360°)

## Applications

- Has a lubricating action on metals and plastics and protects against weather conditions, low acids and bases, and general wear and tear.
- To be used at low pressure levels.
- Applications: door and window hinges, nuts and screws, garden tools, sliding and rolling shutters, etc.
- Not to be used for brake drums and brake discs.

## Packaging

Colour: transparent

Packaging: 400 ml aerosol

## Shelf life

3 years in unopened packaging in a dry and cool environment at temperatures between +5°C and +25°C.

## Substrates

*Nature:* clean, free of dust and grease.  
All types of metals and plastics.

## Application method

*Application method:* Surfaces must be cleaned, degreased and dry. Shake can well before use. Spray at a distance of appr. 20 cm of the object. Apply a thin layer evenly.

## Health- and Safety Recommendations

Use only in well-ventilated areas. In case of contact with eyes, wash immediately with plenty of water.  
Dangerous. Respect the precautions for use.

## Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.